

Arlon 49581XC010 0.0105" (0.267 mm) Uncured Silicone Rubber with Fiberglass Substrate

Category : Polymer , Thermoset , Silicone , Silicone Rubber , Silicone, Molded, Glass Fiber Filled

Material Notes:

Design/Construction: Side 1: Uncured Silicone Rubber Side 2: Uncured Silicone Rubber Appearance: Gray gum on glass fiber fabric This data Represents typical values for the production material. The data should not be used to write, or in place of, material specifications. Information provided by Arlon, Silicone Technologies Division

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-49581XC010-00105-0267-mm-Uncured-Silicone-Rubber-with-Fiberglass-Substrate.php

Physical Properties	Metric	English	Comments
Thickness	>= 63.5 microns	>= 2.50 mil	Side 1
	>= 63.5 microns	>= 2.50 mil	Side 2
	76.2 microns	3.00 mil	Polyethylene, Interleave
	140 microns	5.50 mil	Prime Coated 1681 Fiberglass, Substrate
	241 - 292 microns	9.50 - 11.5 mil	Overall

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	40 - 50	40 - 50	Compound Property
Tensile Strength	>= 5.52 MPa	>= 800 psi	Compound Property
Elongation at Break	>= 500 %	>= 500 %	Compound Property
Peel Strength	>= 1.05 kN/m	>= 6.00 pli	Bond Strength

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	200 °C	392 °F	rated per UL card E54153
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	
Flammability, UL94	HB	HB	Compound Rated

Electrical Properties	Metric	English	Comments
Dielectric Strength	>= 15.7 kV/mm	>= 400 kV/in	

Processing Properties	Metric	English	Comments
	120 min	2.00 hour	

Cure Time Processing Properties	Metric @ Temperature 204 °C	English @ Temperature 400 °F	Recommended Postcure Cycle Comments
	15.0 min	0.250 hour	Recommended Cure Cycle
	@Pressure 0.345 MPa, Temperature 177 °C	@Pressure 50.0 psi, Temperature 350 °F	
Shelf Life	6.00 Month	6.00 Month	From date of manufacture
	@Temperature 23.9 °C	@Temperature 75.0 °F	

Descriptive Properties	Value	Comments
Color	Light Gray	
Total Product Weight (oz/yd2)	9.9 -11.9	
Uncoated Fabric Break Strength	110 lb/in	Fill Direction, Substrate Property
	195 lb/in	Warp Direction, Substrate Property

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China