

Arlon 51279R020 0.020" (0.508 mm) Cured/Uncured Silicone Rubber with Fiberglass Substrate

Category : Polymer , Thermoset , Silicone , Silicone Rubber , Silicone, Molded, Glass Fiber Filled

Material Notes:

Design/Construction: Interleave: Polyethylene Layer 2: Uncured Silicone Rubber Layer 1: Cured Silicone Rubber Substrate: Style 7628

Fiberglass This data represents typical values for the production material. The data should not be used to write, or in place of, material specifications. Information provided by Arlon, Silicone Technologies Division

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-51279R020-0020-0508-mm-CuredUncured-Silicone-Rubber-with-Fiberglass-Substrate.php

Physical Properties	Metric	English	Comments
Density	1.35 g/cc	0.0488 lb/in ³	Silicone Property; Arlon SQA-TMS-024
Thickness	76.2 microns	3.00 mil	Layer 1; Arlon SQA-TMS-003
	76.2 microns	3.00 mil	Interleave
	203 microns	8.00 mil	Substrate; Arlon SQA-TMS-003
	229 microns	9.00 mil	Layer 2; Arlon SQA-TMS-003
	508 microns	20.0 mil	Overall; Arlon SQA-TMS-003

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	60	60	Silicone Property; ASTM D2240
Tensile Strength	5.52 MPa	800 psi	Silicone Property; ASTM D412
Elongation at Break	225 %	225 %	Silicone Property; ASTM D412
Tear Strength	15.8 kN/m	90.0 pli	Die B, Silicone Property; ASTM D624
Peel Strength	1.45 kN/m	8.30 pli	Bond Strength; Arlon-SQA-TMS-011

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	232 °C	450 °F	
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	
UL RTI, Electrical	220 °C	428 °F	E54153
UL RTI, Mechanical without Impact	220 °C	428 °F	E54153

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Dielectric Strength Electrical Properties	27.6 kV/mm Metric	700 kV/in English	Comments
----------------------------------------------	----------------------	----------------------	----------

Processing Properties	Metric	English	Comments
Cure Time	120 min	2.00 hour	Recommended Postcure Cycle
	@Temperature 204 °C	@Temperature 400 °F	
	15.0 min	0.250 hour	Recommended Cure Cycle
	@Pressure 0.345 MPa, Temperature 121 °C	@Pressure 50.0 psi, Temperature 250 °F	
Shelf Life	6.00 Month	6.00 Month	From date of manufacture
	@Temperature 21.1 °C	@Temperature 70.0 °F	

Descriptive Properties	Value	Comments
Color	Red	
	Red	Substrate
Total Product Weight (oz/yd2)	20.9	Arlon SQA-TMS-025

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China