

Arlon 55589G028 0.0295" (0.749 mm) Uncured/Cured Silicone Rubber with Fiberglass Substrate

Category : Polymer , Thermoset , Silicone , Silicone Rubber , Silicone, Molded, Glass Fiber Filled

Material Notes:

Design/Construction: Interleave: Polyethylene Layer 2: Uncured Silicone Rubber Layer 1: Cured Silicone Rubber Substrate: 162 Style

Fiberglass Appearance: Green silicone gum and rubber on fiberglass This data represents typical values for the production material. The data should not be used to write, or in place of, material specifications. Information provided by Arlon, Silicone Technologies Division

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-55589G028-00295-0749-mm-UncuredCured-Silicone-Rubber-with-Fiberglass-Substrate.php

Physical Properties	Metric	English	Comments
Density	1.34 g/cc	0.0484 lb/in ³	Layer 1, Silicone Property; Arlon SQA-TMS-024
	1.56 g/cc	0.0564 lb/in ³	Layer 2, Silicone Property; Arlon SQA-TMS-024
Thickness	76.2 microns	3.00 mil	Interleave
	102 microns	4.00 mil	Layer 1; Arlon SQA-TMS-003
	191 microns	7.50 mil	Layer 2; Arlon SQA-TMS-003
	457 microns	18.0 mil	Substrate; Arlon SQA-TMS-003
	749 microns	29.5 mil	Overall; Arlon SQA-TMS-003

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	37	37	Layer 1, Silicone Property; ASTM D2240
	55	55	Layer 2, Silicone Property; ASTM D2240
Tensile Strength	3.65 MPa	530 psi	Layer 2, Silicone Property; ASTM D412
	6.55 MPa	950 psi	Layer 1, Silicone Property; ASTM D412
Elongation at Break	300 %	300 %	Layer 2, Silicone Property; ASTM D412
	620 %	620 %	Layer 1, Silicone Property; ASTM D412
Tear Strength	7.01 kN/m	40.0 pli	Layer 2, Silicone Property; ASTM D624
	26.3 kN/m	150 pli	Layer 1, Silicone Property; ASTM D624

Peel Strength Mechanical Properties	2.37 kN/m Metric	13.5 psi English	Bond Strength; ASTM D624 Comments
--	---------------------	---------------------	--------------------------------------

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	232 °C	450 °F	
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	
Flammability, UL94	HB @Temperature 200 °C	HB @Temperature 392 °F	per card E54153

Electrical Properties	Metric	English	Comments
Dielectric Strength	17.3 kV/mm	440 kV/in	ASTM D149

Processing Properties	Metric	English	Comments
Cure Time	120 min @Temperature 204 °C	2.00 hour @Temperature 400 °F	Recommended Postcure Cycle
	15.0 min @Pressure 0.345 MPa, Temperature 177 °C	0.250 hour @Pressure 50.0 psi, Temperature 350 °F	Recommended Cure Cycle
Shelf Life	6.00 Month @Temperature 23.9 °C	6.00 Month @Temperature 75.0 °F	From date of manufacture

Descriptive Properties	Value	Comments
Color	Green	
Total Product Weight (oz/yd2)	33.3	Arlon SQA-TMS-025

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China