

Arlon 55596R030 0.030" (0.762 mm) Uncured/Cured Silicone Rubber with Fiberglass Substrate

Category : Polymer , Thermoset , Silicone , Silicone Rubber , Silicone, Molded, Glass Fiber Filled

Material Notes:

Design/Construction: Side 1: Cured Silicone Rubber Side 2: Uncured Silicone Rubber This data Represents typical values for the production material. The data should not be used to write, or in place of, material specifications Information provided by Arlon, Silicone Technologies Division

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-55596R030-0030-0762-mm-UncuredCured-Silicone-Rubber-with-Fiberglass-Substrate.php

Physical Properties	Metric	English	Comments
Thickness	76.2 microns	3.00 mil	Polyethylene, Interleave
	>= 127 microns	>= 5.00 mil	Side 1
	>= 178 microns	>= 7.00 mil	Side 2
	457 microns	18.0 mil	Prime Coated 162 Fiberglass, Substrate
	762 - 838 microns	30.0 - 33.0 mil	Overall

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	40 - 50	40 - 50	Compound Property
Tensile Strength	5.58 - 6.83 MPa	810 - 990 psi	Compound Property
Elongation at Break	540 - 660 %	540 - 660 %	Compound Property
Peel Strength	>= 1.05 kN/m	>= 6.00 pli	Bond Strength

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	232 °C	450 °F	
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	>= 15.7 kV/mm	>= 400 kV/in	

Processing Properties	Metric	English	Comments
Cure Time	120 min	2.00 hour	Recommended Postcure Cycle
	@Temperature 204 °C	@Temperature 400 °F	

Processing Properties	Metric	English	Comments
	@Pressure 0.345 MPa, Temperature 177 °C	@Pressure 50.0 psi, Temperature 350 °F	Recommended Cure Cycle
Shelf Life	6.00 Month @Temperature 23.9 °C	6.00 Month @Temperature 75.0 °F	From date of manufacture

Descriptive Properties	Value	Comments
Color	Red	
Total Product Weight (oz/yd2)	37.5 - 43.5	
Uncoated Fabric Break Strength	420 lb/in	Fill Direction, Substrate Property
	700 lb/in	Warp Direction, Substrate Property

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China