

Arlon 55900R030 0.030" (0.762 mm) Uncured Silicone Rubber with Fiberglass Substrate

Category : Polymer , Thermoset , Silicone , Silicone Rubber , Silicone, Molded, Glass Fiber Filled

Material Notes:

Design/Construction: Interleave: PolyethyleneSide 1: Uncured Silicone Rubber Substrate: 162 Style Fiberglass Appearance: Red silicone gum on glass fabricThis data represents typical values for the production material. The data should not be used to write, or in place of, material specificationsInformation provided by Arlon, Silicone Technologies Division

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-55900R030-0030-0762-mm-Uncured-Silicone-Rubber-with-Fiberglass-Substrate.php

Physical Properties	Metric	English	Comments
Density	1.21 g/cc	0.0437 lb/in ³	Silicone Property; Arlon SQA-TMS-024
Thickness	76.2 microns	3.00 mil	Interleave
	305 microns	12.0 mil	Side 1; Arlon SQA-TMS-003
	457 microns	18.0 mil	Substrate; Arlon SQA-TMS-003
	762 microns	30.0 mil	Overall; Arlon SQA-TMS-003

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	39	39	Silicone Property; ASTM D2240
Tensile Strength	5.52 MPa	800 psi	Silicone Property; ASTM D412
Elongation at Break	700 %	700 %	Silicone Property; ASTM D412
Peel Strength	2.10 kN/m	12.0 pli	Bond Strength; ASTM D624

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	232 °C	450 °F	
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	120 min	2.00 hour	Recommended Postcure Cycle
	@Temperature 204 °C	@Temperature 400 °F	
	15.0 min	0.250 hour	Recommended Cure Cycle
	@Pressure 0.345 MPa, Temperature 177 °C	@Pressure 50.0 psi, Temperature 350 °F	

Processing Properties	6.00 Month Metric	6.00 Month English	Comments
	@Temperature 23.9 °C	@Temperature 75.0 °F	From date of manufacture

Descriptive Properties	Value	Comments
Color	Red	
Total Product Weight (oz/yd2)	34	Arlon SQA-TMS-025

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China