

## Arlon 56606R026 0.027" Cured/Uncured Silicone Rubber with Fiberglass Substrate

Category : Polymer , Thermoset , Silicone , Silicone, Molded, Glass Fiber Filled

### Material Notes:

Design/Construction: Side 1: Cured Silicone Rubber Substrate: Style 1564 Fiberglass Side 2: Uncured Silicone Rubber Interleave: 3 mil PET  
This data represents typical values for the production material and should not be used as material specifications. Information provided by ARLON Silicone Technologies Division.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Arlon-56606R026-0027-CuredUncured-Silicone-Rubber-with-Fiberglass-Substrate.php](http://www.lookpolymers.com/polymer_Arlon-56606R026-0027-CuredUncured-Silicone-Rubber-with-Fiberglass-Substrate.php)

Physical Properties	Metric	English	Comments
Density	1.26 g/cc	0.0455 lb/in <sup>3</sup>	Silicone Property; Arlon SQA-TMS-024
Thickness	102 microns	4.00 mil	Side 1; Arlon SQA-TMS-003
	127 microns	5.00 mil	Side 2; Arlon SQA-TMS-003
	457 microns	18.0 mil	Substrate
	686 microns	27.0 mil	Overall Thickness; Arlon SQA-TMS-003

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	59	59	Silicone Property; ASTM D2240
Tensile Strength	7.86 MPa	1140 psi	Silicone Property; ASTM D412
Elongation at Break	340 %	340 %	Silicone Property; ASTM D412
Tear Strength	17.0 kN/m	97.0 pli	Silicone Property; ASTM D624
Peel Strength	1.75 kN/m	10.0 pli	Bond Strength; ASTM D624

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Inert	232 °C	450 °F	
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	
Flammability, UL94	HB	HB	at 220°C per card E54153

Electrical Properties	Metric	English	Comments
Dielectric Strength	13.8 kV/mm	350 kV/in	ASTM D149

Processing Properties	Metric	English	Comments
Cure Time	120 min	2.00 hour	Recommended Post Cure Cycle
	@Temperature 204 °C	@Temperature 400 °F	
Shelf Life	15.0 min	0.250 hour	Recommended Cure Cycle
	@Pressure 0.345 MPa, Temperature 177 °C	@Pressure 50.0 psi, Temperature 350 °F	
Shelf Life	6.00 Month	6.00 Month	
	@Temperature 23.9 °C	@Temperature 75.0 °F	

Descriptive Properties	Value	Comments
Color	Red	
Total Product Weight (oz/yd2)	30	Arlon SQA-TMS-025

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China