

Arlon CP-494 Bulk Compound

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

This data represents typical values for the production material. The data should not be used to write, or in place of, material specifications. Information provided by Arlon, Silicone Technologies Division

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-CP-494-Bulk-Compound.php

Physical Properties	Metric	English	Comments
Density	1.33 g/cc	0.0480 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	40 - 50	40 - 50	Compound Property
Tensile Strength	>= 6.89 MPa	>= 1000 psi	Compound Property
Elongation at Break	>= 450 %	>= 450 %	Compound Property

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	232 °C	450 °F	
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	
Flammability, UL94	V-0	V-0	Compound Rated per UL Card 109181

Electrical Properties	Metric	English	Comments
Dielectric Strength	>= 15.7 kV/mm	>= 400 kV/in	

Processing Properties	Metric	English	Comments
Cure Time	15.0 - 20.0 min	0.250 - 0.333 hour	Recommended Cure Cycle
	@Temperature 121 - 177 °C	@Temperature 250 - 350 °F	
	120 min	2.00 hour	Recommended Postcure Cycle
	@Temperature 204 °C	@Temperature 400 °F	
Shelf Life	6.00 Month	6.00 Month	From date of manufacture
	@Temperature 23.9 °C	@Temperature 75.0 °F	

Descriptive Properties	Value	Comments
------------------------	-------	----------

Color Descriptive Properties	Brown Value	Comments
---------------------------------	----------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China