

Arlon HSLW301R##-P0 0.030" (0.762 mm) Self-Fusing Silicone Tape (Triangular, Unsupported)

Category : Polymer , Thermoset , Silicone , Silicone Rubber

Material Notes:

Description: High Strength, 1 inch wide, 30 mil thick, Red, Triangular cross-section, Self-Fusing Silicone Tape. Product is supplied in various roll lengths and the ## in the product number indicates roll length in yards. Design/Construction: Rubber: Cured Self-Fusing Silicone Rubber Cross-Section: 1" Wide Triangular Interleave: Polyethylene Appearance: Red silicone rubber on polymer liner This data represents typical values for the production material. The data should not be used to write, or in place of, material specifications. Information provided by Arlon, Silicone Technologies Division

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-HSLW301R-P0-0030-0762-mm-Self-Fusing-Silicone-Tape-Triangular-Unsupported.php

Physical Properties	Metric	English	Comments
Density	1.17 g/cc	0.0423 lb/in ³	Silicone Property; Arlon SQA-TMS-024
Water Absorption	2.0 %	2.0 %	MIL-I-46852C
Thickness	76.2 microns	3.00 mil	Interleave
	762 microns	30.0 mil	Rubber; Arlon SQA-TMS-003

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	55	55	Silicone Property; ASTM D2240
Tensile Strength	8.27 MPa	1200 psi	Silicone Property; ASTM D412
Elongation at Break	450 %	450 %	Silicone Property; ASTM D412
Peel Strength	0.684 kN/m	3.90 pli	Bond Strength; MIL-I-46852C

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	204 °C	400 °F	
Minimum Service Temperature, Air	-51.1 °C	-60.0 °F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	22.4 kV/mm	570 kV/in	ASTM D149

Processing Properties	Metric	English	Comments
Shelf Life	12.0 Month	12.0 Month	From date of manufacture

Processing Properties	@Temperature 23.9 °C Metric	@Temperature 75.0 °F English	Comments
Descriptive Properties	Value		Comments
Allis-Chalmers Tack	1/16 [in]		Arlon SQA-TMS-013
Color	Red		

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China