

## Arlon R3758R0055 0.065" Cured Silicone Rubber with Fiberglass Substrate

Category : Polymer , Thermoset , Silicone , Silicone, Molded, Glass Fiber Filled

### Material Notes:

Design/Construction: Interleave: 1.5 mil Polyethylene Side 1: Cured Silicone Rubber Substrate: Style 2113 Fiberglass This data represents typical values for the production material and should not be used as material specifications. Information provided by ARLON Silicone Technologies Division.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Arlon-R3758R0055-0065-Cured-Silicone-Rubber-with-Fiberglass-Substrate.php](http://www.lookpolymers.com/polymer_Arlon-R3758R0055-0065-Cured-Silicone-Rubber-with-Fiberglass-Substrate.php)

Physical Properties	Metric	English	Comments
Density	1.30 g/cc	0.0470 lb/in <sup>3</sup>	Silicone Property; Arlon SQA-TMS-024
Thickness	38.1 microns	1.50 mil	Interleave
	50.8 microns	2.00 mil	Side 1; Arlon SQA-TMS-003
	50.8 microns	2.00 mil	Substrate; Arlon SQA-TMS-003
	140 microns	5.50 mil	Overall thickness; Arlon SQA-TMS-003

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	60	60	Silicone Property; ASTM D2240
Tensile Strength	5.72 MPa	830 psi	Silicone Property; ASTM D412
Elongation at Break	150 %	150 %	Silicone Property; ASTM D412
Tear Strength	9.64 kN/m	55.0 pli	Die B; Silicone Property; ASTM D624

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Inert	232 °C	450 °F	
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	
Flammability Test	1.0	1.0	Flame and Glow (seconds); FAR 25.853 App.F, P.1, S.Aii
	2.0	2.0	Char Length (inches); FAR 25.853 App.F, P.1, S.Aii

Electrical Properties	Metric	English	Comments
Dielectric Strength	25.0 kV/mm	635 kV/in	ASTM D149

Processing Properties	Metric	English	Comments
Cure Time	120 min	2.00 hour	Recommended Post Cure Cycle
	@Temperature 204 °C	@Temperature 400 °F	
Shelf Life	60.0 Month	60.0 Month	
	@Temperature 23.9 °C	@Temperature 75.0 °F	

Descriptive Properties	Value	Comments
Color	Red	
Total Product Weight (oz/yd2)	6	Arlon SQA-TMS-025

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China