

Asahi Glass AFLAS® SP TFE/P/VdF Fluoroelastomer

Category : Polymer , Thermoset , Fluoropolymer, TS , Thermoset Fluoroelastomer , Rubber or Thermoset Elastomer (TSE)

Material Notes:

AFLAS® SZ/SP are terpolymers containing tetrafluoroethylene, propylene, and a small amount of vinylidene fluoride used as a cure site monomer. This combination gives AFLAS® SZ/SP a good balance of chemical resistance and improved processability when compared to AFLAS® 100/150 dipolymers. AFLAS® SZ is bisphenol-cured, while AFLAS® SP is peroxide-cured. Both polymers are categorized in ASTM D 1481-01 as class FKM, type four. Information provided by Asahi Glass Company, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Asahi-Glass-AFLAS-SP-TFEPVdF-Fluoroelastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.51 g/cc	1.51 g/cc	ASTM D792
Mooney Viscosity	75 @Temperature 100 °C	75 @Temperature 212 °F	ML1+10

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	76	76	
Tensile Strength at Break	18.2 MPa	2640 psi	ASTM D638
Elongation at Break	220 %	220 %	ASTM D638
Compression Set	36 % @Temperature 200 °C	36 % @Temperature 392 °F	70h

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	-3.00 °C	26.6 °F	

Descriptive Properties	Value	Comments
Fluorine Content %	55	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China