

Ascend Performance Materials Vydyn[®] 21SPF BLK Nylon 66, Conditioned

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66 , Unreinforced

Material Notes:

Vydyn[®] 21SPF BLK is a, general-purpose PA66 resin used for extrusion-compounding. Available in black, it is designed principally for injection-molding fabrication. This grade offers a well-balanced combination of engineering properties characterized by high strength; rigidity; good toughness; high melt point; good surface lubricity; abrasion resistance and resistance to many chemicals, machine and motor oils, solvents and gasoline. Vydyn 21SPF BLK resin permits production of molded parts with good initial color plus good property and color retention when using regrind. This resin is recognized by Underwriters Laboratories and conforms to the requirements of many industrial, federal and military specifications for premium-quality, general-purpose PA66 resins. Vydyn 21SPF BLK resin is internally and externally lubricated for improved machine feed and exceptional mold release. In many applications, the molding cycle can be reduced because parts may be removed from the cavity at higher temperatures. In difficult molds where parts have a tendency to stick in the cavity. Vydyn 21SPF BLK can reduce or eliminate the need for mold release sprays. Critical molded part dimensions should be checked against specifications before implementing shorter molding cycles on a routine production basis. Availability:Asia PacificEuropeNorth America Additive:Lubricant Features:Fast Molding CycleGasoline ResistanceGood Abrasion ResistanceGood Chemical ResistanceGood Mold Release Good ToughnessHigh RigidityHigh StrengthLubricated Oil ResistantSolvent ResistantUses: BearingsBushingsCamsConnectorsElectrical Housings Industrial ApplicationsAppearance: BlackForms: PelletsProcessing Method: Injection MoldingInformation provided by Ascend Performance Materials.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ascend-Performance-Materials-Vydyn-21SPF-BLK-Nylon-66-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	ISO 1183
Water Absorption	1.2 % @Time 86400 sec	1.2 % @Time 24.0 hour	ISO 62
Moisture Absorption at Equilibrium	2.4 %	2.4 %	50% RH; ISO 62
Linear Mold Shrinkage, Flow	0.020 cm/cm @Diameter 2.00 mm	0.020 in/in @Diameter 0.0787 in	ISO 294-4
Linear Mold Shrinkage, Transverse	0.020 cm/cm @Diameter 2.00 mm	0.020 in/in @Diameter 0.0787 in	ISO 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	60.0 MPa	8700 psi	ISO 527-2
Tensile Strength, Yield	88.0 MPa	12800 psi	ISO 527-2
Elongation at Break	20 %	20 %	ISO 527-2
Elongation at Yield	5.0 %	5.0 %	ISO 527-2

Mechanical Properties	Metric	English	Comments
Flexural Strength	105 MPa	15200 psi	ISO 178
Flexural Modulus	3.30 GPa	479 ksi	ISO 178
Poissons Ratio	0.40	0.40	ISO 527-2
Izod Impact, Notched (ISO)	5.00 kJ/m ²	2.38 ft-lb/in ²	ISO 180
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	6.00 kJ/m ²	2.86 ft-lb/in ²	ISO 180
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact Unnotched	NB	NB	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	NB	NB	ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.500 J/cm ²	2.38 ft-lb/in ²	ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	0.600 J/cm ²	2.86 ft-lb/in ²	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	10.0 μm/m-°C	5.56 μin/in-°F	ISO 11359-2
	@Thickness 2.00 mm, Temperature 23.0 - 55.0 °C	@Thickness 0.0787 in, Temperature 73.4 - 131 °F	
CTE, linear, Transverse to Flow	10.0 μm/m-°C	5.56 μin/in-°F	ISO 11359-2
	@Thickness 2.00 mm, Temperature 23.0 - 55.0 °C	@Thickness 0.0787 in, Temperature 73.4 - 131 °F	
Melting Point	260 °C	500 °F	ISO 11357-3
Deflection Temperature at 0.46 MPa (66 psi)	201 °C	394 °F	Unannealed; ISO 75-2/B
Deflection Temperature at 1.8 MPa (264 psi)	72.0 °C	162 °F	Unannealed; ISO 75-2/A
UL RTI, Electrical	130 °C	266 °F	UL 746
	@Thickness 0.400 mm	@Thickness 0.0157 in	
	130 °C	266 °F	

Thermal Properties	Metric @Thickness 0.710 mm	English @Thickness 0.0280 in	UL 746 Comments
	130 °C	266 °F	UL 746
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	130 °C	266 °F	UL 746
	@Thickness 3.00 mm	@Thickness 0.118 in	
UL RTI, Mechanical with Impact	75.0 °C	167 °F	UL 746
	@Thickness 0.400 mm	@Thickness 0.0157 in	
	75.0 °C	167 °F	UL 746
	@Thickness 0.710 mm	@Thickness 0.0280 in	
	75.0 °C	167 °F	UL 746
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	75.0 °C	167 °F	UL 746
	@Thickness 3.00 mm	@Thickness 0.118 in	
UL RTI, Mechanical without Impact	75.0 °C	167 °F	UL 746
	@Thickness 0.400 mm	@Thickness 0.0157 in	
	85.0 °C	185 °F	UL 746
	@Thickness 0.710 mm	@Thickness 0.0280 in	
	85.0 °C	185 °F	UL 746
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	85.0 °C	185 °F	UL 746
	@Thickness 3.00 mm	@Thickness 0.118 in	
Flammability, UL94	V-2	V-2	
	@Thickness 0.400 mm	@Thickness 0.0157 in	
	V-2	V-2	
	@Thickness 0.710 mm	@Thickness 0.0280 in	
	V-2	V-2	
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	V-2	V-2	
	@Thickness 3.00 mm	@Thickness 0.118 in	
Oxygen Index	26 %	26 %	ISO 4589-2

Thermal Properties	700 °C Metric	1290 °F English	Ignition Temperature; IEC 60695-2-13
	@Thickness 0.710 mm	@Thickness 0.0280 in	
	700 °C	1290 °F	Ignition Temperature; IEC 60695-2-13
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	700 °C	1290 °F	Ignition Temperature; IEC 60695-2-13
	@Thickness 3.00 mm	@Thickness 0.118 in	
	800 °C	1470 °F	Flammability Index; IEC 60695-2-12
	@Thickness 0.710 mm	@Thickness 0.0280 in	
	800 °C	1470 °F	Flammability Index; IEC 60695-2-12
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	930 °C	1710 °F	Flammability Index; IEC 60695-2-12
	@Thickness 3.00 mm	@Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+10 ohm-cm	1.00e+10 ohm-cm	IEC 60093
	@Thickness 3.00 mm	@Thickness 0.118 in	
Dielectric Strength	26.0 kV/mm	660 kV/in	IEC 60243
	@Thickness 1.00 mm	@Thickness 0.0394 in	
Arc Resistance	120 - 179 sec	120 - 179 sec	ASTM D495
	@Thickness 3.00 mm	@Thickness 0.118 in	
Comparative Tracking Index	600 V	600 V	IEC 60112
	@Thickness 3.00 mm	@Thickness 0.118 in	
Hot Wire Ignition, HWI	7.0 - 14 sec	7.0 - 14 sec	UL 746
	@Thickness 0.710 mm	@Thickness 0.0280 in	
	15 - 29 sec	15 - 29 sec	UL 746
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	15 - 29 sec	15 - 29 sec	UL 746
	@Thickness 3.00 mm	@Thickness 0.118 in	
High Amp Arc Ignition, HAI	>= 120 arcs	>= 120 arcs	UL 746
	@Thickness 0.710 mm	@Thickness 0.0280 in	
	>= 120 arcs	>= 120 arcs	UL 746
	@Thickness 1.50 mm	@Thickness 0.0591 in	

Electrical Properties	Metric arcs	English arcs	Comments
	@Thickness 3.00 mm	@Thickness 0.118 in	UL 746
High Voltage Arc-Tracking Rate, HVTR	0.000 - 10.0 mm/min	0.000 - 0.394 in/min	UL 746

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	260 - 280 °C	500 - 536 °F	
Middle Barrel Temperature	270 - 285 °C	518 - 545 °F	
Front Barrel Temperature	280 - 290 °C	536 - 554 °F	
Nozzle Temperature	280 - 300 °C	536 - 572 °F	
Melt Temperature	285 - 300 °C	545 - 572 °F	
Mold Temperature	65.0 - 95.0 °C	149 - 203 °F	
Drying Temperature	<= 70.0 °C	<= 158 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China