

Ascend Performance Materials Vydyne® 50BWFS Nylon 66, Conditioned (2.5% Moisture)

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Unreinforced

Material Notes:

Vydyne® 50BWFS is a general purpose Nylon 66 resin. Available in natural. Designed for extrusion applications that do not require use of a highviscosity resin. This resin offers a well-balanced combination of engineering properties characterized by high strength, rigidity, good toughness, high melt point, good surface lubricity, and abrasion resistance. Vydyne 50BWFS maintains the chemical resistance typical of nylon to many chemicals, solvents, gasoline, and machine and motor oils. This resin is manufactured as an undried feedstock with a maximum moisture level of 0.5%. Vydyne 50BWFS permits the manufacturing of parts with good initial color plus good property and color retention when using regrind. This resin is recognized by Underwriters Laboratories and conforms to the requirements of many industrial, federal, and military specifications for premium-quality general purpose Nylon 66 resins. Typical Applications/End Uses. Vydyne 50BWFS has been successfully extruded in applications that do not require high melt strength, such as monofilament and bristle products.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ascend-Performance-Materials-Vydyne-50BWFS-Nylon-66-Conditioned-25-Moisture.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.14 g/cc	1.14 g/cc	ISO 1183
Water Absorption	1.3 %	1.3 %	ISO 62
	@Time 86400 sec	@Time 24.0 hour	
Moisture Absorption at Equilibrium	2.4 %	2.4 %	50% RH; ISO 62
Linear Mold Shrinkage	0.012 cm/cm	0.012 in/in	ISO 294-4
	@Thickness 2.00 mm	@Thickness 0.0787 in	
Linear Mold Shrinkage, Transverse	0.014 cm/cm	0.014 in/in	ISO 294-4
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	56.0 MPa	8120 psi	ISO 527
Elongation at Break	>= 100 %	>= 100 %	ISO 527
Elongation at Yield	20 %	20 %	ISO 527
Tensile Modulus	1.40 GPa	203 ksi	ISO 527
Flexural Strength	20.0 MPa	2900 psi	ISO 178
Flexural Modulus	1.36 GPa	197 ksi	ISO 178

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China