

## Asia International Enterprise (Hong Kong) 60G8 Nylon 66, 40% Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 40% Glass Fiber Filled

### Material Notes:

Information provided by Asia International Enterprise (Hong Kong) Ltd.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Asia-International-Enterprise-Hong-Kong-60G8-Nylon-66-40-Filled.php](http://www.lookpolymers.com/polymer_Asia-International-Enterprise-Hong-Kong-60G8-Nylon-66-40-Filled.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.50 g/cc	1.50 g/cc	ASTM D792
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Filler Content	40 %	40 %	
Linear Mold Shrinkage	0.0030 - 0.0050 cm/cm	0.0030 - 0.0050 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	122	122	ASTM D785
Tensile Strength, Ultimate	216 MPa	31300 psi	5mm/min; ASTM D638
Elongation at Break	2.0 %	2.0 %	5mm/min; ASTM D638
Flexural Strength	299 MPa	43400 psi	2.8mm/min; ASTM D790
Flexural Modulus	12.3 GPa	1780 ksi	2.8mm/min; ASTM D790
Izod Impact, Notched	1.27 J/cm	2.39 ft-lb/in	ASTM D256
	@Thickness 3.17 mm, Temperature 23.0 °C	@Thickness 0.125 in, Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	261 °C	502 °F	ASTM D789
Deflection Temperature at 0.46 MPa (66 psi)	262 °C	504 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	252 °C	486 °F	ASTM D648
Flammability, UL94	HB	HB	

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	250 - 300 °C	482 - 572 °F	Cylinder Temperature
Mold Temperature	50.0 - 90.0 °C	122 - 194 °F	

Processing Properties	Metric <sup>90.0 °C</sup>	English <sup>176.0 °F</sup>	Comments
Dry Time	4 - 6 hour	4 - 6 hour	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China