

Azoty Tarnow™ TARFLEN SM-B30 PTFE

Category : Polymer , Thermoplastic , Fluoropolymer , PTFE , Polytetrafluoroethylene (PTFE), Bronze Filled

Material Notes:

Reinforced with 30% bronze for standard compression molding. Information provided by Zakłady Azotowe w Tarnowie-Moscicach S.A.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Azoty-Tarnow-TARFLEN-SM-B30-PTFE.php

Physical Properties	Metric	English	Comments
Density	2.80 g/cc	0.101 lb/in ³	ISO 1183
Filler Content	30 %	30 %	Bronze Filler
Particle Size	40 µm	40 µm	Average

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	58	58	ISO 868
Ball Indentation Hardness	36.0 MPa	5220 psi	ISO 2039-1
Tensile Strength, Yield	20.0 MPa	2900 psi	ISO 527
Elongation at Break	310 %	310 %	ISO 527
Izod Impact, Notched	1.30 J/cm	2.44 ft-lb/in	ISO 180

Thermal Properties	Metric	English	Comments
CTE, linear	65.0 µm/m-°C @Temperature 20.0 °C	36.1 µin/in-°F @Temperature 68.0 °F	ASTM E 831
Melting Point	327 °C	621 °F	
Flammability, UL94	V-0	V-0	

Processing Properties	Metric	English	Comments
Processing Temperature	360 °C	680 °F	Molding
Back Pressure	40.0 - 60.0 MPa	5800 - 8700 psi	Molding Pressure

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China