

Azoty Tarnow™ TARFLEN SM-K25 PTFE

Category : Polymer , Thermoplastic , Fluoropolymer , PTFE

Material Notes:

Based on Tarflen SM1 reinforced with 25% coke for standard compression molding. Information provided by Zakłady Azotowe w Tarnowie-Moscicach S.A.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Azoty-Tarnow-TARFLEN-SM-K25-PTFE.php

Physical Properties	Metric	English	Comments
Density	2.11 g/cc	0.0762 lb/in ³	ISO 1183
Filler Content	25 %	25 %	Coke
Particle Size	40 µm	40 µm	Average

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	66	66	ISO 868
Ball Indentation Hardness	50.0 MPa	7250 psi	ISO 2039-1
Tensile Strength, Yield	14.0 MPa	2030 psi	ISO 527
Elongation at Break	120 %	120 %	ISO 527
Izod Impact, Notched	1.20 J/cm	2.25 ft-lb/in	ISO 180

Thermal Properties	Metric	English	Comments
CTE, linear	65.0 µm/m-°C	36.1 µin/in-°F	ASTM E 831
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Melting Point	327 °C	621 °F	
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Volume Resistivity	64000 ohm-cm	64000 ohm-cm	IEC 60093
Surface Resistance	64000 ohm	64000 ohm	IEC 60093

Processing Properties	Metric	English	Comments
Processing Temperature	370 °C	698 °F	Molding
Back Pressure	40.0 - 60.0 MPa	5800 - 8700 psi	Molding Pressure

Processing Properties

Metric

English

Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China