

Azoty Tarnow™ TARNOFORM 300 TF2 POM

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, PTFE Filled

Material Notes:

Tribological modified grade with addition of 10% PTFE, which causes decreased coefficient of friction and wear. Information provided by Zakłady Azotowe w Tarnowie-Moscicach S.A.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Azoty-Tarnow-TARNOFORM-300-TF2-POM.php

Physical Properties	Metric	English	Comments
Density	1.46 g/cc	0.0527 lb/in ³	ISO 1183
Melt Flow	8.5 g/10 min @Load 2.16 kg, Temperature 190 °C	8.5 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	55.0 MPa	7980 psi	ISO 527
Elongation at Break	33 %	33 %	ISO 527
Flexural Strength	57.0 MPa	8270 psi	ISO 178
Charpy Impact, Notched	0.500 J/cm ²	2.38 ft-lb/in ²	1eA; ISO 179

Thermal Properties	Metric	English	Comments
Specific Heat Capacity	1.48 J/g-°C	0.354 BTU/lb-°F	
Melting Point	167 °C	333 °F	10°C/min.; ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	112 °C	234 °F	ISO 75
Vicat Softening Point	151 °C	304 °F	50 N; ISO 306
Flammability, UL94	HB @Thickness 3.20 mm	HB @Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+15 ohm	1.00e+15 ohm	IEC 60093
Dielectric Constant	3.8 @Frequency 1e+6 Hz	3.8 @Frequency 1e+6 Hz	IEC 60250

Electrical Properties	Metric	English	Comments
Dissipation Factor	0.010 @Frequency 1e+6 Hz	0.010 @Frequency 1e+6 Hz	IEC 60250
Comparative Tracking Index	600 V	600 V	IEC 112

Processing Properties	Metric	English	Comments
Processing Temperature	180 - 230 °C	356 - 446 °F	Barrel temperature
Mold Temperature	60.0 - 120 °C	140 - 248 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China