

## BASF Capron® B100ZP Nylon 6 (DAM) (discontinued \*\*)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

### Material Notes:

Information provided by BASF Corporation. Capron® is no longer a part of the BASF standard line. The BASF nylon products have been consolidated in the Ultramid® line.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BASF-Capron-B100ZP-Nylon-6-DAM-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_BASF-Capron-B100ZP-Nylon-6-DAM-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in <sup>3</sup>	ISO 1183
Volatiles	0.50 %	0.50 %	Extractable
Water Absorption	1.6 %	1.6 %	24 hr.; ISO 62
	9.5 %	9.5 %	ISO 62
Moisture Absorption at Equilibrium	0.040 %	0.040 %	ASTM D570
	2.7 %	2.7 %	23°C/50% R.H.; ISO 62
Oxygen Transmission Rate	40.3 cc/m <sup>2</sup> /day	2.60 cc/100 in <sup>2</sup> /day	
Nitrogen Transmission	14.0 cc-mm/m <sup>2</sup> -24hr-atm	35.6 cc-mil/100 in <sup>2</sup> -24hr-atm	cc/m <sup>2</sup> /day (Thickness not reported)
Carbon Dioxide Transmission	72.8 cc-mm/m <sup>2</sup> -24hr-atm	185 cc-mil/100 in <sup>2</sup> -24hr-atm	cc/m <sup>2</sup> /day (Thickness not reported)
Viscosity Measurement	3.35	3.35	Relative Viscosity (96% SAV)
	3.4	3.4	Relative Viscosity (95% SAV)
	3.5	3.5	Relative Viscosity (98% SAV)
	100	100	Formic Acid; ASTM D789

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	10 K/min
	220 °C	428 °F	ASTM D3418

Descriptive Properties	Value	Comments
Color	Natural	
Commercial Status (March 2007)	Active America	

FDA Descriptive Properties	21 CFR 177.1500 Value	Comments
Impact Modified	No	
Primary Processing Technique	Film Extrusion	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China