

## BASF Elastollan B 90 A TPUR

Category : Polymer , Thermoplastic , Polyurethane, TP , Thermoplastic Polyurethane (TPUR), Polyester Grade

### Material Notes:

Description: Thermoplastic Polyester Polyurethane Elastomers with excellent mechanical properties, outstanding wear resistance, high tensile strength, good damping and resilience performance and superior low temperature flexibility. Typical Applications: Sport-shoe soles and accessories, ski-boot shells, technical moldings, e.g. seals, castor tyres and tubing. Note: Quoted results are from measurements on injection molded test platens, post tempered for 20 hours at 100°C. Information provided by BASF

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BASF-Elastollan-B-90-A-TPUR.php](http://www.lookpolymers.com/polymer_BASF-Elastollan-B-90-A-TPUR.php)

Physical Properties	Metric	English	Comments
Density	1.21 g/cc	0.0437 lb/in <sup>3</sup>	ISO 1183-1-A

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	91	91	ISO 868
Hardness, Shore D	42	42	ISO 686
Tensile Strength	40.0 MPa	5800 psi	after storage in water at 80°C for 42 days; ISO 37
	55.0 MPa	7980 psi	ISO 37
	4.00 MPa	580 psi	ISO 37
	@Strain 20.0 %	@Strain 20.0 %	
Tensile Strength	7.00 MPa	1020 psi	ISO 37
	@Strain 100 %	@Strain 100 %	
Tensile Strength	20.0 MPa	2900 psi	ISO 37
	@Strain 300 %	@Strain 300 %	
Elongation at Break	550 %	550 %	ISO 37
	550 %	550 %	after storage in water at 80°C for 42 days; ISO 37
Charpy Impact, Notched	NB	NB	DIN EN ISO 179
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	NB	NB	DIN EN ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Tear Strength	90.0 kN/m	514 pli	DIN ISO 34-1/Bb
Abrasion	30	30	[mm<sup>3</sup>; ISO 4649

Mechanical Properties	Metric	English	Comments
Compression Set	@Temperature 23.0 °C	@Temperature 73.4 °F	ISO 815
	40 %	40 %	ISO 815
	@Temperature 70.0 °C	@Temperature 158 °F	

Processing Properties	Metric	English	Comments
Processing Temperature	175 - 230 °C	347 - 446 °F	Injection molding
	175 - 230 °C	347 - 446 °F	Extrusion
Mold Temperature	20.0 - 70.0 °C	68.0 - 158 °F	

Descriptive Properties	Value	Comments
Commercial Status	North America	
Primary Processing Technique	Injection molding and Extrusion	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China