

BASF Elastollan C 65 A HPM TPUR

Category : Polymer , Thermoplastic , Polyurethane, TP , Thermoplastic Polyurethane (TPUR), Polyester Grade

Material Notes:

Description: Thermoplastic Polyester Polyurethane Elastomers with excellent mechanical properties and chemical resistance, outstanding wear resistance, high tear and tensile strength, good damping characteristics and a high resilience performance. Typical Applications: Spiral tubing, pneumatic tubing, round and v-beltting, technical moldings, e.g. bushes, dust caps, seals, blow molding bellows, and mining screens. Note: Quoted results are from measurements on injection molded test platens, post tempered for 20 hours at 100°C. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Elastollan-C-65-A-HPM-TPUR.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in ³	ISO 1183-1-A

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	65	65	ISO 868
Tensile Strength	25.0 MPa	3630 psi	after storage in water at 80°C for 42 days; ISO 37
	40.0 MPa	5800 psi	ISO 37
	1.50 MPa @Strain 20.0 %	218 psi @Strain 20.0 %	ISO 37
	2.00 MPa @Strain 100 %	290 psi @Strain 100 %	ISO 37
Elongation at Break	4.00 MPa @Strain 300 %	580 psi @Strain 300 %	ISO 37
	800 %	800 %	ISO 37
Charpy Impact, Notched	900 %	900 %	after storage in water at 80°C for 42 days; ISO 37
	NB @Temperature -30.0 °C	NB @Temperature -22.0 °F	DIN EN ISO 179
Tear Strength	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	DIN EN ISO 179
	40.0 kN/m	228 pli	DIN ISO 34-1/Bb
Abrasion	40	40	[mm³; ISO 4649

Mechanical Properties	Metric	English	Comments
Compression Set	@Temperature 23.0 °C	@Temperature 73.4 °F	ISO 815
	30 %	30 %	ISO 815
	@Temperature 70.0 °C	@Temperature 158 °F	

Processing Properties	Metric	English	Comments
Processing Temperature	160 - 220 °C	320 - 428 °F	Extrusion
	170 - 240 °C	338 - 464 °F	Injection molding
Mold Temperature	20.0 - 70.0 °C	68.0 - 158 °F	

Descriptive Properties	Value	Comments
Commercial Status	North America	
Primary Processing Technique	Injection molding, Extrusion and Blow molding	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China