

## BASF Elastollan® C-78A Polyester Type Polyurethane Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane, TP , Thermoplastic Polyurethane, Elastomer, Polyester Grade

### Material Notes:

Processed by extrusion or injection molding. Elastollan C series of products are polyester-based thermoplastic polyurethanes that exhibit very good hydrolytic stability. They also exhibit excellent oil, fuel and solvent resistance. These products can be injection and blow molded and extruded. As with all TPU products this grade must be dried prior to processing. Property values below are typical values based on test samples cured 20 hours at 100°C before testing. Information provided by BASF Corporation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BASF-Elastollan-C-78A-Polyester-Type-Polyurethane-Elastomer.php](http://www.lookpolymers.com/polymer_BASF-Elastollan-C-78A-Polyester-Type-Polyurethane-Elastomer.php)

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in <sup>3</sup>	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	80	80	ASTM D2240
Tensile Strength, Ultimate	37.0 MPa	5370 psi	ASTM D412
Tensile Strength, Yield	1.10 MPa @Strain 300 %	160 psi @Strain 300 %	ASTM D-412
	5.20 MPa @Strain 100 %	754 psi @Strain 100 %	ASTM D-412
Elongation at Break	690 %	690 %	ASTM D412
Tear Strength	85.0 kN/m	485 pli	ASTM D624
Taber Abrasion, mg/1000 Cycles	25	25	H-18 wheel; ASTM D-1044.
Tensile Set	25 %	25 %	at break; ASTM D-412

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China