

## **BASF Heligoen® Blue 6989 F Color Additive**

Category : Other Engineering Material , Additive/Filler for Polymer

## Material Notes:

Description: Extremely reddish, e-phthalocyanine blue with high chroma and excellent flocculation resistanceChemical Structure: Cuphthalocyanine, alpha-stabPhysical form: PowderSuitable for: Baking systems, Acrylic-isocyanate systems, Acid curing systems, Amine curing systems, and Airdrying systems.Information provided by BASF

Order this product through the following link: http://www.lookpolymers.com/polymer\_BASF-Heligoen-Blue-6989-F-Color-Additive.php

Density 1.64 g/cc 0.0592 lb/in <sup>3</sup>	Metric English Comments	
	1.64 g/cc 0.0592 lb/in <sup>3</sup>	
Specific Surface Area50 m²/g50 m²/g	50 m²/g 50 m²/g	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	300 °C	572 °F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	>= 5000 ohm-cm	>= 5000 ohm-cm	

Chemical Properties	Metric	English	Comments
Total Acid Number	5.0 - 7.0	5.0 - 7.0	

Descriptive Properties	Value	Comments
Chemical Fastness (months)	Butylacetate	4-5
	Ethanol	3-4
	HCL 2%	5
	Methyl ethyl ketone	4
	Mineral spirits	4-5
	NaOH 2%	5
	Solvenon™PM	4-5
	Xylene	4-5
Color	Blue	
Fastness to Overcoating	5	



Plastic Technology Co., Ltd.

**Descriptive Properties** 

Value

Comments

Contact Songhan Plastic Technology Co.,Ltd. Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China