

BASF Lupranate® 278 Isocyanate

Category : Fluid

Material Notes:

Description: Lupranate® 278 Isocyanate is an isocyanate blend of monomeric and polymeric MDI. Typical use is for flexible slab stock and molded Visco-Elastic memory foams. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Lupranate-278-Isocyanate.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	
Viscosity	17 cP	17 cP	
Vapor Pressure	2.67e-7 bar @Temperature 25.0 °C	0.000200 torr @Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Boiling Point	>= 190 °C @Pressure 0.000667 MPa	>= 374 °F @Pressure 0.0967 psi	
Flash Point	>= 200 °C	>= 392 °F	

Descriptive Properties	Value	Comments
Color	Light Brown	
Composition	NCO content	0.33

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China