

## BASF Neopolen® P 9255 0.09 g/cc Core density; Expanded Polypropylene (Europe)

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Foamed

### Material Notes:

Description: Neopolen® P 9255 is expanded Polypropylene supplied in the form of beads. The cells are largely closed. Physical properties of moldings made from Neopolen® P 9255. Note: In order to measure the physical properties, parts with dimensions 300x200x60 mm were molded on a machine typical for the EPP industry under standard conditions. The properties can vary depending on part geometry and processing parameters. Information provided by BASF

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BASF-Neopolen-P-9255-009-gcc-Core-density-Expanded-Polypropylene-Europe.php](http://www.lookpolymers.com/polymer_BASF-Neopolen-P-9255-009-gcc-Core-density-Expanded-Polypropylene-Europe.php)

Physical Properties	Metric	English	Comments
Bulk Density	0.0500 - 0.0600 g/cc	0.00181 - 0.00217 lb/in <sup>3</sup>	
Density	0.0900 g/cc	0.00325 lb/in <sup>3</sup>	ISO 845
Water Absorption	<= 1.0 % @Time 86400 sec	<= 1.0 % @Time 24.0 hour	DIN 53428
Particle Size	>= 1500 µm	>= 1500 µm	
	<= 4000 µm	<= 4000 µm	

Mechanical Properties	Metric	English	Comments
Tensile Strength	1.28 MPa	186 psi	DIN EN ISO 1798
Elongation at Break	21 %	21 %	DIN EN ISO 1798
Compressive Strength	0.580 MPa @Strain 10.0 %	84.1 psi @Strain 10.0 %	ISO 844
	0.650 MPa @Strain 25.0 %	94.3 psi @Strain 25.0 %	ISO 844
	0.950 MPa @Strain 50.0 %	138 psi @Strain 50.0 %	ISO 844
Compression Set	25 % @Temperature 23.0 °C, Time 79200 sec	25 % @Temperature 73.4 °F, Time 22.0 hour	50% RH; 24h after stress release; DIN EN ISO 1856 (Procedure C)

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Conductivity Thermal Properties	0.0450 W/m-K Metric	0.312 BTU-in/hr-ft <sup>2</sup> -°F English	DIN 52612 Comments
Melting Point	120 - 180 °C	248 - 356 °F	
Decomposition Temperature	>= 180 °C	>= 356 °F	
Flash Point	>= 200 °C	>= 392 °F	ASTM D1929

Descriptive Properties	Value	Comments
Average Particle Weight	1.0 - 1.4 mg	
Color	Black	
Commercial Status	Europe	
Dimensional Stability at Heat	<2%	Linear size alterations after 4 d, 110°C; DIN ISO 2796
Ignition Temperature	> 360 °C	ASTM D1929

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China