

## BASF Novolen® 1126 N Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

**Material Notes:**

Grade with slip and antiblocking agents, for cast and water-cooled blown film with very good slip and especially low tendency to block. Data was collected by ISO methods and provided by BASF.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BASF-Novolen-1126-N-Polypropylene.php](http://www.lookpolymers.com/polymer_BASF-Novolen-1126-N-Polypropylene.php)

Physical Properties	Metric	English	Comments
Density	0.910 g/cc	0.0329 lb/in <sup>3</sup>	
Water Absorption	0.10 %	0.10 %	
Moisture Absorption at Equilibrium	0.10 %	0.10 %	
Melt Flow	15 g/10 min @Load 2.16 kg, Temperature 230 °C	15 g/10 min @Load 4.76 lb, Temperature 446 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	135 µm/m-°C @Temperature 20.0 °C	75.0 µin/in-°F @Temperature 68.0 °F	
Melting Point	163 °C	325 °F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	
Dielectric Constant	2.3 @Frequency 1e+6 Hz	2.3 @Frequency 1e+6 Hz	
Dielectric Strength	140 kV/mm	3560 kV/in	
Dissipation Factor	0.000070 @Frequency 100 Hz	0.000070 @Frequency 100 Hz	
	0.00020 @Frequency 1e+6 Hz	0.00020 @Frequency 1e+6 Hz	
Comparative Tracking Index	600 V	600 V	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**