

## BASF Novolen® 3248 RC Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

### Material Notes:

Grade containing nucleating and antistatic agents for injection molded parts. Data was collected by ISO methods and provided by BASF.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BASF-Novolen-3248-RC-Polypropylene.php](http://www.lookpolymers.com/polymer_BASF-Novolen-3248-RC-Polypropylene.php)

Physical Properties	Metric	English	Comments
Density	0.910 g/cc	0.0329 lb/in <sup>3</sup>	
Water Absorption	0.10 %	0.10 %	
Moisture Absorption at Equilibrium	0.10 %	0.10 %	
Linear Mold Shrinkage, Flow	0.013 cm/cm	0.013 in/in	
Melt Flow	31 g/10 min	31 g/10 min	
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	29.0 MPa	4210 psi	
Elongation at Break	>= 50 %	>= 50 %	
Elongation at Yield	11 %	11 %	
Tensile Modulus	1.10 GPa	160 ksi	
Charpy Impact Unnotched	20.0 J/cm <sup>2</sup>	95.2 ft-lb/in <sup>2</sup>	
	1.30 J/cm <sup>2</sup>	6.19 ft-lb/in <sup>2</sup>	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	0.600 J/cm <sup>2</sup>	2.86 ft-lb/in <sup>2</sup>	
	0.150 J/cm <sup>2</sup>	0.714 ft-lb/in <sup>2</sup>	
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	185 µm/m-°C	103 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Melting Point	150 °C	302 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (64 psi)	70.0 °C	158 °F	
Deflection Temperature at 1.8 MPa (264 psi)	50.0 °C	122 °F	
Vicat Softening Point	72.0 °C	162 °F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	
Surface Resistance	1.00e+10 ohm	1.00e+10 ohm	
Dielectric Constant	2.3	2.3	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	140 kV/mm	3560 kV/in	
Dissipation Factor	0.00081	0.00081	
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.0020	0.0020	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	600 V	600 V	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China