

## BASF Procom® D 1175 Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

**Material Notes:**

Data was collected by ISO methods and provided by BASF.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BASF-Procom-D-1175-Polypropylene.php](http://www.lookpolymers.com/polymer_BASF-Procom-D-1175-Polypropylene.php)

Physical Properties	Metric	English	Comments
Density	1.24 g/cc	0.0448 lb/in <sup>3</sup>	
Linear Mold Shrinkage, Flow	0.011 cm/cm	0.011 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	32.0 MPa	4640 psi	
Elongation at Break	7.0 %	7.0 %	
Tensile Modulus	4.50 GPa	653 ksi	
Charpy Impact Unnotched	1.40 J/cm <sup>2</sup>	6.66 ft-lb/in <sup>2</sup>	
	0.800 J/cm <sup>2</sup>	3.81 ft-lb/in <sup>2</sup>	
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	80.0 µm/m-°C	44.4 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	130 °C	266 °F	
Deflection Temperature at 1.8 MPa (264 psi)	85.0 °C	185 °F	
Vicat Softening Point	105 °C	221 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China