

## BASF Procom® T40H 564 Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

**Material Notes:**

Car heater casings.Data was collected by ISO methods and provided by BASF.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BASF-Procom-T40H-564-Polypropylene.php](http://www.lookpolymers.com/polymer_BASF-Procom-T40H-564-Polypropylene.php)

Physical Properties	Metric	English	Comments
Density	1.24 g/cc	0.0448 lb/in <sup>3</sup>	
Linear Mold Shrinkage, Flow	0.010 cm/cm	0.010 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	34.0 MPa	4930 psi	
Elongation at Break	3.0 %	3.0 %	
Tensile Modulus	4.50 GPa	653 ksi	
Charpy Impact Unnotched	1.50 J/cm <sup>2</sup>	7.14 ft-lb/in <sup>2</sup>	
	0.800 J/cm <sup>2</sup>	3.81 ft-lb/in <sup>2</sup>	
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	55.0 µm/m-°C	30.6 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	130 °C	266 °F	
Deflection Temperature at 1.8 MPa (264 psi)	85.0 °C	185 °F	
Vicat Softening Point	105 °C	221 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China