

BASF Ultraform® N2650 Z4 (LEV) POM

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Unreinforced

Material Notes:

Description: Is a POM + PUR, elastomer-modified injection-molding grades with high impact strength for clips, snap and fastening elements, also for components subject to impact stress. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Ultraform-N2650-Z4-LEV-POM.php

Physical Properties	Metric	English	Comments
Density	1.35 g/cc	0.0488 lb/in ³	ISO 1183
Water Absorption	0.80 %	0.80 %	Saturation; ISO 62
Moisture Absorption at Equilibrium	0.20 %	0.20 %	23°C; 50% RH; ISO 62
Melt Flow	8.1 g/10 min @Load 2.16 kg, Temperature 190 °C	8.1 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	80.0 MPa @Load 36.5 kg, Time 30.0 sec	11600 psi @Load 80.5 lb, Time 0.00833 hour	ISO 2039-1
Tensile Strength, Yield	45.0 MPa	6530 psi	50 mm/min; ISO 527-2
Elongation at Break	40 %	40 %	ISO 527-2
Elongation at Yield	16 %	16 %	ISO 527-2
Modulus of Elasticity	1.50 GPa	218 ksi	ISO 527-2
Izod Impact, Notched (ISO)	7.00 kJ/m ² @Temperature -30.0 °C	3.33 ft-lb/in ² @Temperature -22.0 °F	ISO 180/A
	12.0 kJ/m ² @Temperature 23.0 °C	5.71 ft-lb/in ² @Temperature 73.4 °F	ISO 180/A
Charpy Impact Unnotched	27.0 J/cm ² @Temperature -30.0 °C	128 ft-lb/in ² @Temperature -22.0 °F	ISO 179/1eU
	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	ISO 179/1eU
	0.800 J/cm ²	3.81 ft-lb/in ²	

Charpy Impact, Notched Mechanical Properties	Metric @ Temperature -30.0 °C	English @ Temperature -22.0 °F	ISO 179/1eA Comments
	1.50 J/cm ²	7.14 ft-lb/in ²	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Tensile Creep Modulus, 1000 hours	500 MPa	72500 psi	ISO 899-1

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	13.0 µm/m-°C	7.22 µin/in-°F	DIN 53752
	@Temperature 23.0 - 55.0 °C	@Temperature 73.4 - 131 °F	
Melting Point	167 °C	333 °F	DIN 53765
Maximum Service Temperature, Air	100 °C	212 °F	
Deflection Temperature at 1.8 MPa (264 psi)	80.0 °C	176 °F	ISO 75-2
Vicat Softening Point	130 °C	266 °F	ISO 306

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+11 ohm-cm	1.00e+11 ohm-cm	IEC 60093
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	IEC 60093
Dielectric Constant	4.2	4.2	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	4.3	4.3	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	32.0 kV/mm	813 kV/in	IEC 60243-1
Dissipation Factor	0.012	0.012	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.017	0.017	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	600 V	600 V	Test solution A; IEC 60112
	600 V	600 V	Test solution B; IEC 60112

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Melt Temperature Processing Properties	190 - 215 °C Metric	374 - 419 °F English	Injection-molding Comments
Mold Temperature	60.0 - 80.0 °C	140 - 176 °F	

Descriptive Properties	Value	Comments
Commercial Status	Europe	
Primary Processing Technique	Injection Molding	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China