

BASF Ultraform® S2320 003 PRO BK 00120 POM

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Unreinforced

Material Notes:

Description: Is a POM, is a standard flowing and rapidly freezing grade suitable for standard functional applications. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Ultraform-S2320-003-PRO-BK-00120-POM.php

Physical Properties	Metric	English	Comments
Density	1.40 g/cc	0.0506 lb/in ³	ISO 1183
Water Absorption	0.80 %	0.80 %	Saturation; ISO 62
Moisture Absorption at Equilibrium	0.20 %	0.20 %	23°C; 50% RH; ISO 62
Linear Mold Shrinkage, Flow	0.021 cm/cm	0.021 in/in	ISO 2577
Linear Mold Shrinkage, Transverse	0.021 cm/cm	0.021 in/in	ISO 2577
Melt Flow	13 g/10 min @Load 2.16 kg, Temperature 190 °C	13 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	145 MPa @Load 36.5 kg, Time 30.0 sec	21000 psi @Load 80.5 lb, Time 0.00833 hour	ISO 2039-1
Tensile Strength, Yield	65.0 MPa	9430 psi	50 mm/min; ISO 527-2
Elongation at Break	28 %	28 %	ISO 527-2
Elongation at Yield	9.0 %	9.0 %	ISO 527-1/-2
Modulus of Elasticity	2.70 GPa	392 ksi	ISO 527-2
Izod Impact, Notched (ISO)	5.50 kJ/m ² @Temperature -30.0 °C	2.62 ft-lb/in ² @Temperature -22.0 °F	ISO 180/A
	5.50 kJ/m ² @Temperature 23.0 °C	2.62 ft-lb/in ² @Temperature 73.4 °F	ISO 180/A
Charpy Impact Unnotched	17.0 J/cm ² @Temperature -30.0 °C	80.9 ft-lb/in ² @Temperature -22.0 °F	ISO 179/1eU
	18.0 J/cm ²	85.7 ft-lb/in ²	

Mechanical Properties	Metric	English	ISO 179/1eJ Comments
Charpy Impact, Notched	0.500 J/cm ²	2.38 ft-lb/in ²	ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	0.550 J/cm ²	2.62 ft-lb/in ²	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Tensile Creep Modulus, 1000 hours	1300 MPa	189000 psi	ISO 899-1

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	11.0 µm/m-°C	6.11 µin/in-°F	DIN 53752
	@Temperature 23.0 - 55.0 °C	@Temperature 73.4 - 131 °F	
Melting Point	167 °C	333 °F	
Maximum Service Temperature, Air	100 °C	212 °F	
Deflection Temperature at 1.8 MPa (264 psi)	100 °C	212 °F	ISO 75-2
Vicat Softening Point	150 °C	302 °F	ISO 306

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 ohm-cm	1.00e+13 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093
Dielectric Constant	3.8	3.8	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	3.8	3.8	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	40.0 kV/mm	1020 kV/in	IEC 60243-1
Dissipation Factor	0.0010	0.0010	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.0050	0.0050	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	600 V	600 V	Test solution A; IEC 60112
	600 V	600 V	Test solution B; IEC 60112

Electrical Properties	Metric	English	Comments
Processing Properties	Metric	English	Comments
Melt Temperature	190 - 230 °C	374 - 446 °F	Injection-molding
Mold Temperature	60.0 - 120 °C	140 - 248 °F	
Drying Temperature	100 °C	212 °F	
Dry Time	3 hour	3 hour	

Descriptive Properties	Value	Comments
Color	BK 00120	
Commercial Status	Europe	
Primary Processing Technique	Injection Molding	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China