

BASF Ultramid® B3M6 BK60564 30% Mineral Filled PA6 (Conditioned)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 30% Mineral Filled

Material Notes:

Ultramid B3M6 BK60564 is a 30% mineral reinforced, pigmented black injection molding PA6 grade for industrial items requiring high impact strength and very high dimensional stability, excellent laser markability.

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Ultramid-B3M6-BK60564-30-Mineral-Filled-PA6-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.36 g/cc	0.0491 lb/in ³	ISO 1183
Water Absorption	5.9 - 6.5 %	5.9 - 6.5 %	ISO 62
Moisture Absorption at Equilibrium	2.2 - 2.6 %	2.2 - 2.6 %	(23°C/50% R.H.); ISO 62
Viscosity Measurement	145	145	Viscosity Number; ISO 307
Linear Mold Shrinkage	0.0075 cm/cm	0.0075 in/in	
Melt Flow	81.6 g/10 min @Load 5.00 kg, Temperature 275 °C	81.6 g/10 min @Load 11.0 lb, Temperature 527 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	45.0 MPa	6530 psi	50mm/min; ISO 527
Elongation at Break	55 %	55 %	50mm/min; ISO 527
Modulus of Elasticity	1.70 GPa	247 ksi	ISO 527
Flexural Strength	50.0 MPa	7250 psi	ISO 178
Flexural Modulus	1.40 GPa	203 ksi	ISO 178
Izod Impact, Notched (ISO)	15.0 kJ/m ²	7.14 ft-lb/in ²	ISO 180/A
Charpy Impact Unnotched	NB	NB	ISO 179/1eU
Charpy Impact, Notched	1.80 J/cm ²	8.57 ft-lb/in ²	ISO 179/1eA
Tensile Creep Modulus, 1000 hours	800 MPa @Strain 0.500 %	116000 psi @Strain 0.500 %	ISO 899-1

Thermal Properties	Metric	English	Comments
Specific Heat Capacity	1.40 J/g-°C	0.335 BTU/lb-°F	

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	DIN 53765
Maximum Service Temperature, Air	180 °C	356 °F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+10 ohm-cm	1.00e+10 ohm-cm	IEC 60093
Surface Resistance	1.00e+10 ohm	1.00e+10 ohm	IEC 60093
Dielectric Constant	6.2 @Frequency 1.00e+6 Hz	6.2 @Frequency 1.00e+6 Hz	IEC 60250
Dissipation Factor	0.20 @Frequency 1.00e+6 Hz	0.20 @Frequency 1.00e+6 Hz	IEC 60250
Comparative Tracking Index	450 V	450 V	Test Solution A; IEC 60112

Processing Properties	Metric	English	Comments
Melt Temperature	270 - 290 °C	518 - 554 °F	Injection-molding/Extrusion
Mold Temperature	80.0 - 90.0 °C	176 - 194 °F	Injection-molding

Descriptive Properties	Value	Comments
Color	BK60564	
Commercial Status	North America and Europe	
Impact Modified	No	
Primary Processing Technique	Injection Molding	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China