

BASF Ultrason® E 3010 MR UN PESU

Category : Polymer , Thermoplastic , Polyethersulfone (PES)

Material Notes:

Description: Unreinforced, higher viscosity injection molding and extrusion grade with improved toughness and chemical resistance (stress crack resistance); demolding optimized. Abbreviated designation according to ISO 1043-1: PESInformation provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Ultrason-E-3010-MR-UN-PESU.php

Physical Properties	Metric	English	Comments
Bulk Density	0.700 - 0.800 g/cc	0.0253 - 0.0289 lb/in ³	
Density	1.37 g/cc	0.0495 lb/in ³	ISO 1183
Water Absorption	2.2 %	2.2 %	ISO 62
Moisture Absorption at Equilibrium	0.80 %	0.80 %	23°C; 50% RH; ISO 62
Viscosity Measurement	66	66	[cm³/g]; ISO 307
Linear Mold Shrinkage, Flow	0.0085 cm/cm	0.0085 in/in	ISO 2577, 294-4
Linear Mold Shrinkage, Transverse	0.0090 cm/cm	0.0090 in/in	ISO 2577, 294-4
Melt Flow	47.95 g/10 min @Load 10.0 kg, Temperature 360 °C	47.95 g/10 min @Load 22.0 lb, Temperature 680 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	154 MPa @Load 36.5 kg, Time 30.0 sec	22300 psi @Load 80.5 lb, Time 0.00833 hour	ISO 2039-1
Tensile Strength, Yield	90.0 MPa	13100 psi	50mm/min; ISO 527-1/-2
Elongation at Yield	6.7 %	6.7 %	50mm/min; ISO 527-1/-2
Izod Impact, Notched (ISO)	7.00 kJ/m ² @Temperature -30.0 °C	3.33 ft-lb/in ² @Temperature -22.0 °F	ISO 180/A
	7.50 kJ/m ² @Temperature 23.0 °C	3.57 ft-lb/in ² @Temperature 73.4 °F	ISO 180/A
Charpy Impact Unnotched	NB @Temperature -30.0 °C	NB @Temperature -22.0 °F	ISO 179/1eU
	NB	NB	

Mechanical Properties	Metric @ Temperature 23.0 °C	English @ Temperature 73.4 °F	ISO 179/1eJ Comments
Charpy Impact, Notched	0.750 J/cm ²	3.57 ft-lb/in ²	ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	0.750 J/cm ²	3.57 ft-lb/in ²	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Tensile Creep Modulus, 1000 hours	2700 MPa	392000 psi	ISO 899-1

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	52.0 µm/m-°C	28.9 µin/in-°F	ISO 75-1/-2
	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	
	59.0 µm/m-°C	32.8 µin/in-°F	DIN 53752
	@Temperature 180 °C	@Temperature 356 °F	
Maximum Service Temperature, Air	180 °C	356 °F	at 50% loss of tensile strength after 20000 hr
	220 °C	428 °F	
Deflection Temperature at 1.8 MPa (264 psi)	207 °C	405 °F	ISO 75-1/-2
Glass Transition Temp, Tg	228 °C	442 °F	ISO 11357-1/-2
Decomposition Temperature	>= 400 °C	>= 752 °F	
Flammability, UL94	V-0	V-0	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	V-0	V-0	
	@Thickness 3.10 mm	@Thickness 0.122 in	

Optical Properties	Metric	English	Comments
Refractive Index	1.63	1.63	ISO 489
	@Thickness 1.00 mm	@Thickness 0.0394 in	
Transmission, Visible	88 %	88 %	DIN 5036-3

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+13 ohm-cm	>= 1.00e+13 ohm-cm	IEC 60093
	3.8	3.8	

Dielectric Constant Electrical Properties	Metric @Frequency 1.00e+6 Hz	English @Frequency 1.00e+6 Hz	ISO 60250 Comments
	3.9	3.9	ISO 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	34.0 kV/mm	864 kV/in	0
Dissipation Factor	0.00170	0.00170	
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.0140	0.0140	
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	100 V	100 V	Test Liquid A; IEC 60112
	100 V	100 V	Test Liquid B; IEC 60112

Processing Properties	Metric	English	Comments
Processing Temperature	80.0 °C	176 °F	Hopper throat
Zone 1	350 °C	662 °F	Feed zone
Zone 2	360 °C	680 °F	Compression
Zone 3	370 °C	698 °F	Metering-zone
Zone 4	370 °C	698 °F	Nozzle
Melt Temperature	350 - 390 °C	662 - 734 °F	Injection molding/extrusion
	370 °C	698 °F	Optimal
Mold Temperature	140 - 180 °C	284 - 356 °F	Injection molding
	160 °C	320 °F	Optimal

Descriptive Properties	Value	Comments
Commercial Status	Europe	
Ignition Temperature	580-600°C	DIN 54836
Primary Processing Technique	Injection molding, Extrusion and Blow molding	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China