

BP Amoco Acclear® 6219 Homopolymer Polypropylene, High Clarity Grade (discontinued **)

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Extrusion Grade

Material Notes:

Suggested fabrication methods: Sheet extrusion; Thermoforming
 Features: High clarity, High heat resistance, Good melt strength/flow balance
 Typical applications: Rigid packaging
 Complies with FDA specification, Title 21, CFR 177.1520. Typical property data below from injection molded samples.

Order this product through the following link:

http://www.lookpolymers.com/polymer_BP-Amoco-Acclear-6219-Homopolymer-Polypropylene-High-Clarity-Grade-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.886 - 0.926 g/cc	0.0320 - 0.0335 lb/in ³	ASTM D1505
Water Absorption	<= 0.010 %	<= 0.010 %	24 hours; ASTM D570
Linear Mold Shrinkage	0.010 - 0.025 cm/cm	0.010 - 0.025 in/in	ASTM D955
Melt Flow	2.2 g/10 min @Load 2.16 kg, Temperature 230 °C	2.2 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	39.0 MPa	5660 psi	ASTM D638
Flexural Modulus	1.65 GPa	239 ksi	ASTM D790A
Izod Impact, Notched	0.320 J/cm @Diameter 3.17 mm	0.599 ft-lb/in @Diameter 0.125 in	bar; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	116 °C	241 °F	ASTM D648

Optical Properties	Metric	English	Comments
Haze	23 % @Thickness 1.27 mm	23 % @Thickness 0.0500 in	plaque; ASTM D1003
Transmission, Visible	90 %	90 %	clear; thickness not quantified

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China