

Bapolene® 152A Polyethylene Film Grade

Category : Polymer , Thermoplastic , Polyethylene (PE) , LLDPE

Material Notes:

Bapolene 152A is a hexene linear low density polyethylene with a combination of superior impact strength and HSIT. Product is designed to exhibit performance similar to that of metallocene products. It complies with US FDA 21CFR177.1520. Antiblock addition distinguishes 152A from 152B.Applications: General purpose packaging, trash bags, and liners.Bapolene® and Bapolan® are registered trademarks of Bamberger Polymers, Inc. Information provided by Bamberger Polymers

Order this product through the following link:
http://www.lookpolymers.com/polymer_Bapolene-152A-Polyethylene-Film-Grade.php

Physical Properties	Metric	English	Comments
Density	0.915 g/cc	0.0331 lb/in³	ASTM D-1505
Thickness	25.4 microns	1.00 mil	2.5:1 BUR as tested
Melt Flow	0.70 g/10 min @Load 2.16 kg, Temperature 190 °C	0.70 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238
Antiblock Level	6850 ppm	6850 ppm	
Slip Level	0.000 ppm	0.000 ppm	

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	650 %	650 %	ASTM D-882
Film Elongation at Break, TD	860 %	860 %	ASTM D-882
Elmendorf Tear Strength MD	450 g	450 g	ASTM D-1922
Elmendorf Tear Strength TD	600 g	600 g	ASTM D-1922
Elmendorf Tear Strength, MD	17.7 g/micron	450 g/mil	ASTM D-1922
Elmendorf Tear Strength, TD	23.6 g/micron	600 g/mil	ASTM D-1922
Dart Drop Test	525 g	1.16 lb	F₅₀; ASTM D-1709
Film Tensile Strength at Break, MD	38.0 MPa	5510 psi	ASTM D-882
Film Tensile Strength at Break, TD	34.0 MPa	4930 psi	ASTM D-882
Heat Seal Strength Initiation Temperature	103 °C	217 °F	0.5 s dwell; 2 lb_f/in

Descriptive Properties	Value	Comments
------------------------	-------	----------

Process Descriptive Properties	Film Value	Comments
Region	Europe/Turkey	Bamberger Polymers Distribution
	International	Bamberger Polymers Distribution
	Mexico	Bamberger Polymers Distribution
	US & Canada	Bamberger Polymers Distribution

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China