

## Barlog Plastics KEBAFLOW MF130 LCP, 30% glass fiber reinforced

Category : Polymer , Thermoplastic , Liquid Crystal Polymer (LCP) , Liquid Crystal Polymer (LCP), 30% Glass Fiber Filled

**Material Notes:**

LCP-GF30 Information provided by BARLOG plastics GmbH.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Barlog-Plastics-KEBAFLOW-MF130-LCP-30-glass-fiber-reinforced.php](http://www.lookpolymers.com/polymer_Barlog-Plastics-KEBAFLOW-MF130-LCP-30-glass-fiber-reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.62 g/cc	0.0585 lb/in <sup>3</sup>	ISO 1183
Water Absorption	0.040 %	0.040 %	similar to ISO 62 test
Linear Mold Shrinkage, Flow	0.0016 cm/cm	0.0016 in/in	ISO 294-4
Linear Mold Shrinkage, Transverse	0.0038 cm/cm	0.0038 in/in	ISO 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	145 MPa	21000 psi	ISO 527-1
Elongation at Break	1.9 %	1.9 %	ISO 527-1
Tensile Modulus	14.5 GPa	2100 ksi	ISO 527-1

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	270 °C	518 °F	ISO 75-1/-2
Flammability, UL94	V-0 @Thickness 0.800 mm	V-0 @Thickness 0.0315 in	UL Registered; IEC 60695-11-10

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 ohm-cm	1.00e+13 ohm-cm	IEC 60093
Surface Resistance	1.00e+15 ohm	1.00e+15 ohm	IEC 60093

Descriptive Properties	Value	Comments
Resin Type	LCP-GF30	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**