

Barlog Plastics KEBAFORM C 901 FA POM Copolymer unreinforced, reduced formaldehyde emission

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Unreinforced

Material Notes:

POM information provided by BARLOG plastics GmbH.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Barlog-Plastics-KEBAFORM-C-901-FA-POM-Copolymer-unreinforced-reduced-formaldehyde-emission.php

Physical Properties	Metric	English	Comments
Density	1.41 g/cc	0.0509 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	0.22 %	0.22 %	similar to ISO 62 test
Linear Mold Shrinkage, Flow	0.020 cm/cm	0.020 in/in	ISO 294-4
Linear Mold Shrinkage, Transverse	0.020 cm/cm	0.020 in/in	ISO 294-4
Melt Flow	9.0 g/10 min @Load 2.16 kg, Temperature 190 °C	9.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	65.0 MPa	9430 psi	ISO 527-1
Elongation at Yield	9.0 %	9.0 %	ISO 527-1
Tensile Modulus	2.70 GPa	392 ksi	ISO 527-1
Charpy Impact Unnotched	NB	NB	ISO 179-1eU
Charpy Impact, Notched	0.700 J/cm ²	3.33 ft-lb/in ²	ISO 179-1eA

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	120 µm/m-°C	66.7 µin/in-°F	ISO 11359-1/-2
CTE, linear, Transverse to Flow	120 µm/m-°C	66.7 µin/in-°F	ISO 11359-1/-2
Melting Point	166 °C	331 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 0.46 MPa (66 psi)	160 °C	320 °F	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	110 °C	230 °F	ISO 75-1/-2
Flammability, UL94	HB	HB	IEC 60695-11-10

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	IEC 60093
Surface Resistance	1.00e+16 ohm	1.00e+16 ohm	IEC 60093

Descriptive Properties	Value	Comments
Resin Type	POM	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China