

Beijing Ranger Chem 0191S Solid Epoxy Resin

Category : Polymer , Thermoset , Epoxy , Epoxy Cure Resin

Material Notes:

Information provided by Beijing Ranger Chemical Co.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Beijing-Ranger-Chem-0191S-Solid-Epoxy-Resin.php

Thermal Properties	Metric	English	Comments
Softening Point	65.0 - 75.0 °C	149 - 167 °F	

Descriptive Properties	Value	Comments
Epoxy Equivalent g/eq	455-500	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China