

Borealis BorECO™ BA222E Polypropylene Block Copolymer for Non-Pressure Pipes

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Extrusion Grade

Material Notes:

BorECO BA222E is a high molecular weight, low melt flow rate polypropylene block copolymer with superior stiffness and excellent impact properties. BorECO BA222E fulfills the requirements according to EN 1852-1/A1 and is a PP-HM (polypropylene high modulus) material. BorECO BA222E is recommended for solid wall non-pressure piping especially in underground drainage and sewerage and soil and waste applications. Information provided by the Manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Borealis-BorECO-BA222E-Polypropylene-Block-Copolymer-for-Non-Pressure-Pipes.php

Physical Properties	Metric	English	Comments
Density	0.915 g/cc	0.0331 lb/in ³	ISO 1183
Melt Flow	0.25 g/10 min @Load 2.16 kg, Temperature 230 °C	0.25 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	33.00 MPa	4786 psi	At 50 mm/min; ISO 527-2
Elongation at Yield	8.0 %	8.0 %	At 50 mm/min; ISO 527-2
Flexural Modulus	1.90 GPa	276 ksi	At 2 mm/min; ISO 178
Charpy Impact, Notched	5.00 J/cm ²	23.8 ft-lb/in ²	ISO 179/1eA
	0.400 J/cm ² @Temperature -20.0 °C	1.90 ft-lb/in ² @Temperature -4.00 °F	ISO 179/1eA

Processing Properties	Metric	English	Comments
Front Barrel Temperature	200 - 220 °C	392 - 428 °F	
Die Temperature	210 - 220 °C	410 - 428 °F	
Melt Temperature	210 - 230 °C	410 - 446 °F	
Head Temperature	210 - 220 °C	410 - 428 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China