

Borealis BorPEX™ ME2510 Medium Density Polyethylene Compound for Crosslinked Pipes (Pex-B (Silane))

Category : Polymer , Thermoplastic , Polyethylene (PE) , MDPE , Medium Density Polyethylene (MDPE), Molded

Material Notes:

BorPEX ME2510 is a silane crosslinkable compound which is used together with a catalyst masterbatch (Cat-MB) to accelerate the moisture-induced crosslinking reaction. It is designed for crosslinkable pipes with superior flexibility. BorPEX ME2510 is designed for the requirements in DIN 16 892/DIN 16 887 and prEN ISO 15 875 for hot and cold water pressure pipes, e.g. floor heating, radiator connections and for domestic hot and cold water supply. Information provided by the Manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Borealis-BorPEX-ME2510-Medium-Density-Polyethylene-Compound-for-Crosslinked-Pipes-Pex-B-Silane.php

Physical Properties	Metric	English	Comments
Density	0.935 g/cc	0.0338 lb/in ³	ISO 1183
Melt Flow	1.0 g/10 min @Load 5.00 kg, Temperature 190 °C	1.0 g/10 min @Load 11.0 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	15.0 MPa	2180 psi	At 50 mm/min; ISO/DIS 6259
Tensile Strength, Yield	20.00 MPa	2901 psi	At 50 mm/min; ISO/DIS 6259
Elongation at Break	180 %	180 %	ISO/DIS 6259
Elongation at Yield	13 %	13 %	ISO/DIS 6259
Modulus of Elasticity	0.630 GPa	91.4 ksi	ISO 527

Thermal Properties	Metric	English	Comments
CTE, linear	90.0 µm/m-°C	50.0 µin/in-°F	ASTM D696
	@Temperature -20.0 °C	@Temperature -4.00 °F	
	140 µm/m-°C	77.8 µin/in-°F	ASTM D696
	@Temperature 20.0 °C	@Temperature 68.0 °F	
	500 µm/m-°C	278 µin/in-°F	ASTM D696
	@Temperature 100 °C	@Temperature 212 °F	
Specific Heat Capacity	2.10 J/g-°C	0.502 BTU/lb-°F	
Thermal Conductivity	0.410 W/m-K	2.85 BTU-in/hr-ft ² -°F	DIN 52612

Vicat Softening Point
Thermal Properties

122 °C
Metric

252 °F
English

ISO 305
Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China