

Borealis Visico™ LE4421/LE4460/LE4432 Scorch Retardant, Moisture-Crosslinking Polyethylene Compound for Low Voltage Installation

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Wire/Cable Grade

Material Notes:

Visico LE4421/LE4460/LE4432 is a black, halogen-based flame retardant, moisture-induced crosslinking polyethylene compound that is designed for use as low voltage wire insulation and jacketing. The combination of the Visico LE4421 base resin, along with the LE4460 brominated flame retardant masterbatch and the LE4432 tin catalyst masterbatch provides a highly scorch retardant compound with excellent thermal stability and good flame properties. LE4421/LE4460/LE4432 contains a patented scorch retardant additive (SRA) that increases the processing window for a moisture crosslinking compound that minimizes the tendency for premature crosslinking in the extruder, head or die. A finished compound that is composed of 70 parts LE4421 mixed with 20 parts of LE4460 and 10 parts of LE4432 is recognized by Underwriters Laboratories as Visico Horizontal. LE4421/LE4460/LE4432 is recommended for use as insulation for low voltage control cables and power cables up to 6 kV in rating. Information provided by the Manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Borealis-Visico-LE4421LE4460LE4432-Scorch-Retardant-Moisture-Crosslinking-Polyethylene-Compound-for-Low-Voltage-Installation.php

Physical Properties	Metric	English	Comments
Density	0.923 g/cc	0.0333 lb/in ³	LE 4421; ASTM D792
	1.05 g/cc	0.0379 lb/in ³	LE 4432; ASTM D792
	2.00 g/cc	0.0723 lb/in ³	LE 4460; ASTM D792
Melt Flow	0.90 g/10 min	0.90 g/10 min	LE 4421; ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	>= 14.58 MPa	>= 2115 psi	Heat Aging (7 days at 121°C); ASTM D412
	16.2 MPa	2350 psi	ASTM D412
	<= 50 %	<= 50 %	Hot Creep Test (150°C, .2 MPa); ICEA T-28-562
Elongation at Break	270 %	270 %	Heat Aging (7 days at 121°C); ASTM D412
	300 %	300 %	ASTM D412
	<= 5.0 %	<= 5.0 %	Hot Creep Test (150°C, .2 MPa); ICE T-28-562
Tensile Set	<= 5.0 %	<= 5.0 %	Hot Creep Test (150°C, .2 MPa); ICE T-28-562

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257
	2.3	2.3	

Dielectric Constant Electrical Properties	Metric @Frequency 60 Hz	English @Frequency 60 Hz	ASTM D150 Comments
Dielectric Strength	>= 21.7 kV/mm	>= 550 kV/in	ASTM D149
Dissipation Factor	0.00050 @Frequency 60 Hz	0.00050 @Frequency 60 Hz	ASTM D150

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	>= 171 °C	>= 340 °F	
Front Barrel Temperature	>= 146 °C	>= 295 °F	
Die Temperature	>= 177 °C	>= 350 °F	
Head Temperature	>= 177 °C	>= 351 °F	

Descriptive Properties	Value	Comments
Horizontal Flame Test	Pass	14AWG-30mil, UL 1581

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China