

## Braskem H 501 HC Bioriented Film Polypropylene

Category : Polymer , Film , Thermoplastic , Polypropylene (PP) , Polypropylene, Film Grade

**Material Notes:**

Applications: High stiffness; barrier films for conversion Information provided by Braskem

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Braskem-H-501-HC-Bioriented-Film-Polypropylene.php](http://www.lookpolymers.com/polymer_Braskem-H-501-HC-Bioriented-Film-Polypropylene.php)

Physical Properties	Metric	English	Comments
Density	0.905 g/cc	0.0327 lb/in <sup>3</sup>	ASTM D792A
Melt Flow	3.5 g/10 min @Load 2.16 kg, Temperature 230 °C	3.5 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238L

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	93	93	ASTM D785
Tensile Strength, Yield	38.0 MPa	5510 psi	ASTM D638
Elongation at Yield	8.0 %	8.0 %	ASTM D638
Flexural Modulus	2.04 GPa	296 ksi	ASTM D790
Izod Impact, Notched	0.310 J/cm @Temperature 23.0 °C	0.581 ft-lb/in @Temperature 73.4 °F	ASTM D256A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	110 °C	230 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	62.0 °C	144 °F	ASTM D648
Vicat Softening Point	158 °C	316 °F	-1kg; ASTM D1525

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China