

## Braskem LH 0820/30 AF LLDPE Blown Film Extrusion Polyethylene

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Film Grade

### Material Notes:

38µm film gauge, obtained in 40mm extruder, with blow up ratio 2, 2:1 Applications: Lamination; heavy duty bags; blends with LDPE and HDPE; valvulated heavy duty bags. Information provided by Braskem

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Braskem-LH-082030-AF-LLDPE-Blown-Film-Extrusion-Polyethylene.php](http://www.lookpolymers.com/polymer_Braskem-LH-082030-AF-LLDPE-Blown-Film-Extrusion-Polyethylene.php)

Physical Properties	Metric	English	Comments
Density	0.920 g/cc	0.0332 lb/in <sup>3</sup>	ASTM D1505
Thickness	38.0 microns	1.50 mil	
Melt Flow	0.80 g/10 min @Load 2.16 kg, Temperature 190 °C	0.80 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	947 %	947 %	ASTM D882
Film Elongation at Break, TD	1185 %	1185 %	ASTM D882
Secant Modulus, MD	0.174 GPa	25.2 ksi	1%; ASTM D882
Secant Modulus, TD	0.184 GPa	26.7 ksi	1%; ASTM D882
Coefficient of Friction	0.67	0.67	ASTM D1894
Elmendorf Tear Strength, MD	11.0 g/micron	279 g/mil	ASTM 1922
Elmendorf Tear Strength, TD	20.0 g/micron	508 g/mil	ASTM 1922
Dart Drop	4.55 g/micron	116 g/mil	ASTM D1709
Film Tensile Strength at Break, MD	47.0 MPa	6820 psi	ASTM D882
Film Tensile Strength at Break, TD	37.0 MPa	5370 psi	ASTM D882

Optical Properties	Metric	English	Comments
Haze	34.8 %	34.8 %	ASTM D1003
Gloss	4.9 %	4.9 %	60° angle; ASTM D2457

Descriptive Properties	Value	Comments
Additives	Antiblock and PPA	

Descriptive Properties	Value	Comments
Minimum Recommended Thickness	50 µm	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China