

Braskem LL6802N LLDPE Blown Film Extrusion Polyethylene Copolymer

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE)/Octene, Film

Material Notes:

LL6802N resin is a linear low-density polyethylene, copolymer of octene-1, produced by the solution process for blown film extrusion with excellent mechanical properties. It contains processing aid and antioxidant additives. Its applications include: heavy-duty bags, liners, LDPE and HDPE blends, and packages for general use. LL6802N resin should be processed on specific extruders for LLDPE. The best results are obtained at a melt temperature within the range of 200 to 220° and blends with LDPE with a maximum ratio of 30%. Recommended blow up ratio: 1.8 to 3:1.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Braskem-LL6802N-LLDPE-Blown-Film-Extrusion-Polyethylene-Copolymer.php

Physical Properties	Metric	English	Comments
Density	0.925 g/cc	0.0334 lb/in ³	ASTM-D792
Melt Flow	0.65 g/10 min @Load 2.16 kg, Temperature 190 °C	0.65 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM-D1238

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	800 %	800 %	ASTM-D882
Film Elongation at Break, TD	1130 %	1130 %	ASTM-D882
Elmendorf Tear Strength MD	140 g	140 g	ASTM-D1922
Elmendorf Tear Strength TD	460 g	460 g	ASTM-D1922
Elmendorf Tear Strength, MD	5.60 g/micron	142 g/mil	ASTM-D1922
Elmendorf Tear Strength, TD	18.4 g/micron	467 g/mil	ASTM-D1922
Dart Drop	5.20 g/micron	132 g/mil	ASTM-D1709
Dart Drop Test	130 g	0.287 lb	ASTM-D1709
Film Tensile Strength at Break, MD	40.0 MPa	5800 psi	ASTM-D882
Film Tensile Strength at Break, TD	30.0 MPa	4350 psi	ASTM-D882
1% Secant Modulus, MD	230 MPa	33400 psi	ASTM-D882
1% Secant Modulus, TD	270 MPa	39200 psi	ASTM-D882

Optical Properties	Metric	English	Comments
Haze	8.0 %	8.0 %	ASTM-D1003

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China