

C.O.I.M. EXTER S® S 111 B Orthophthalic Resin

Category : Polymer , Thermoset , Polyester, TS , Polyester (Thermoset) - Rigid

Material Notes:

Description: The Exter S product line contains a large number of unsaturated polyester resin products with an array of properties and applications. Specific Notes for EXTER S® S 111 B: Low viscosity resin for injection technology Information provided by P.A.T. Products, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_COIM-EXTER-S-S-111-B-Orthophthalic-Resin.php

Physical Properties	Metric	English	Comments
Brookfield Viscosity	120 - 160 cP @Temperature 25.0 °C	120 - 160 cP @Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	75.0 - 80.0 °C	167 - 176 °F	

Chemical Properties	Metric	English	Comments
Styrene Content	42 - 44 %	42 - 44 %	

Descriptive Properties	Value	Comments
Rigidity	medium	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China