

C.O.I.M. EXTER S® S 201 Special Laminate

Category : Polymer , Thermoset , Polyester, TS , Polyester (Thermoset) - Rigid

Material Notes:

Description: The Exter S product line contains a large number of unsaturated polyester resin products with an array of properties and applications. Specific Notes for ESTER S® S 201: Polyester resin TMPDE based for varnishes Information provided by P.A.T. Products, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_COIM-EXTER-S-S-201-Special-Laminate.php

Physical Properties	Metric	English	Comments
Brookfield Viscosity	1400 - 1800 cP	1400 - 1800 cP	
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	90.0 - 95.0 °C	194 - 203 °F	

Chemical Properties	Metric	English	Comments
Styrene Content	23 - 27 %	23 - 27 %	

Descriptive Properties	Value	Comments
Rigidity	medium/low	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China