

CP-Polymer-Technik Wellamid® 6600 HW Nylon 66, Heat Stabilized, Conditioned

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Unreinforced

Material Notes:

Information provided by CP-Polymer-Technik GmbH & Co. KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_CP-Polymer-Technik-Wellamid-6600-HW-Nylon-66-Heat-Stabilized-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	2.5 - 3.0 %	2.5 - 3.0 %	23°C/50%RH, Starting when dry; DIN 53495
Linear Mold Shrinkage	0.0080 - 0.012 cm/cm @Thickness 4.00 mm	0.0080 - 0.012 in/in @Thickness 0.157 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	55.0 MPa	7980 psi	50 mm/min; ISO 527
Elongation at Break	>= 50 %	>= 50 %	50 mm/min; ISO 527
Elongation at Yield	15 %	15 %	50 mm/min; ISO 527
Tensile Modulus	1.10 GPa	160 ksi	ISO 527
Charpy Impact Unnotched	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	ISO 179
Charpy Impact, Notched	1.50 J/cm ² @Temperature 23.0 °C	7.14 ft-lb/in ² @Temperature 73.4 °F	ISO 179

Thermal Properties	Metric	English	Comments
Melting Point	255 °C	491 °F	Kofler

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+12 ohm-cm	1.00e+12 ohm-cm	IEC 93
Surface Resistance	1.00e+10 ohm	1.00e+10 ohm	ISO 3915
Dielectric Constant	5.0 @Frequency 1e+6 Hz	5.0 @Frequency 1e+6 Hz	IEC 250

Dielectric Strength Electrical Properties	30.0 kV/mm Metric	762 kV/in English	IEC 243-1 Comments
Dielectric Loss Index	0.20	0.20	At 1 MHz; IEC 250

Processing Properties	Metric	English	Comments
Melt Temperature	260 - 290 °C	500 - 554 °F	
Mold Temperature	50.0 - 90.0 °C	122 - 194 °F	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Holding Pressure	High	
Injection Speed	Medium to High	
Screw Speed	High	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China