

Chang Chun Plastic PBT2100 Fire Retardant PBT

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), Flame Retardant

Material Notes:

Information provided by Dowell Trading Company Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chang-Chun-Plastic-PBT2100-Fire-Retardant-PBT.php

Physical Properties	Metric	English	Comments
Density	1.42 - 1.44 g/cc	0.0513 - 0.0520 lb/in ³	ASTM D792
Water Absorption	0.050 %	0.050 %	24 hour immersion; ASTM D570
Linear Mold Shrinkage	0.013 - 0.020 cm/cm	0.013 - 0.020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	88	88	ASTM D785
Tensile Strength, Ultimate	50.0 - 70.0 MPa	7250 - 10200 psi	ASTM D638
Elongation at Break	4.0 - 6.0 %	4.0 - 6.0 %	ASTM D638
Flexural Yield Strength	90.0 - 120 MPa	13100 - 17400 psi	ASTM D790
Flexural Modulus	2.50 - 3.50 GPa	363 - 508 ksi	ASTM D790
Izod Impact, Notched	0.250 - 0.340 J/cm @Thickness 6.35 mm	0.468 - 0.637 ft-lb/in @Thickness 0.250 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	90.0 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$ @Temperature 20.0 $^\circ\text{C}$	50.0 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$ @Temperature 68.0 $^\circ\text{F}$	ASTM D696
Melting Point	225 $^\circ\text{C}$	437 $^\circ\text{F}$	DSC
Deflection Temperature at 0.46 MPa (66 psi)	165 $^\circ\text{C}$	329 $^\circ\text{F}$	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	65.0 $^\circ\text{C}$	149 $^\circ\text{F}$	ASTM D648
Flammability, UL94	V-0	V-0	1/32 in.

Electrical Properties	Metric	English	Comments
Electrical Resistivity	$\geq 1.00\text{e}+16$ ohm-cm	$\geq 1.00\text{e}+16$ ohm-cm	ASTM D257

Surface Resistance Electrical Properties	$\geq 1.00e+14$ ohm Metric	$\geq 1.00e+14$ ohm English	ASTM D257 Comments
Dielectric Constant	3.2 @Frequency 60 Hz	3.2 @Frequency 60 Hz	ASTM D150
Dielectric Strength	18.0 kV/mm @Thickness 2.00 mm	457 kV/in @Thickness 0.0787 in	ASTM D149
Dissipation Factor	0.0010 @Frequency 60 Hz	0.0010 @Frequency 60 Hz	ASTM D150
Arc Resistance	120 sec	120 sec	ASTM D495

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China