

Chase Plastics CP Pryme® ASA300 BK General Purpose (Utility) ASA Molding Resin

Category : Polymer , Thermoplastic , ASA Polymer , Acrylonitrile/Styrene/Acrylate (ASA), Unreinforced, Molded

Material Notes:

Information provided by Chase Plastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chase-Plastics-CP-Pryme-ASA300-BK-General-Purpose-Utility-ASA-Molding-Resin.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.07 g/cc	1.07 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	43.4 MPa	6300 psi	ASTM D638
Elongation at Break	18 %	18 %	ASTM D638
Flexural Strength	74.5 MPa	10800 psi	ASTM D790
Flexural Modulus	2.25 GPa	326 ksi	ASTM D790
Izod Impact, Notched	1.87 J/cm	3.50 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	90.6 °C	195 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China