

Chase Plastics CP Pryme® NN100MD2 (COND, 50% RH) Nylon 66 with 2% MoS2 Lubricated

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, MoS2 Filled

Material Notes:

Information provided by Chase Plastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chase-Plastics-CP-Pryme-NN100MD2-COND-50-RH-Nylon-66-with-2-MoS2-Lubricated.php

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	68.3 MPa	9900 psi	ASTM D638
Elongation at Break	>= 50 %	>= 50 %	ASTM D638
Flexural Strength	71.7 MPa	10400 psi	ASTM D790
Flexural Modulus	1.69 GPa	245 ksi	ASTM D790
Izod Impact, Notched	1.33 J/cm	2.50 ft-lb/in	ASTM D256

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China