

Chase Plastics CP Pryme® NN343L (Dry) Nylon 66, 43% Glass Fiber Reinforced, Lubricated, Recycled Content

Category : Polymer , Renewable/Recycled Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 40% Glass Fiber Filled

Material Notes:

Features: Recycled content
Form: Pellets
Information provided by Chase Plastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chase-Plastics-CP-Pryme-NN343L-Dry-Nylon-66-43-Glass-Fiber-Reinforced-Lubricated-Recycled-Content.php

Physical Properties	Metric	English	Comments
Density	1.50 g/cc	0.0542 lb/in ³	ASTM D792
Filler Content	43 %	43 %	
Water Absorption	0.80 %	0.80 %	At 24 hrs; ASTM D570
Linear Mold Shrinkage, Flow	0.0030 - 0.0050 cm/cm	0.0030 - 0.0050 in/in	0.125 in; ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	100	100	ASTM D785
Tensile Strength at Break	200 MPa	29000 psi	ASTM D638
Elongation at Break	2.0 %	2.0 %	ASTM D638
Flexural Strength	303 MPa	44000 psi	ASTM D790
Flexural Modulus	10.0 GPa	1450 ksi	ASTM D790
Izod Impact, Notched	1.23 J/cm	2.30 ft-lb/in	0.125 in; ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	
Deflection Temperature at 1.8 MPa (264 psi)	249 °C	480 °F	Unannealed; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China