

Cheng Yu Plastic T885GV3 Flame Retardant PBT, 30% Glass Fiber

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 30% Glass Fiber Filled

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cheng-Yu-Plastic-T885GV3-Flame-Retardant-PBT-30-Glass-Fiber.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.60 g/cc	1.60 g/cc	ASTM D792
Linear Mold Shrinkage	0.0050 - 0.020 cm/cm	0.0050 - 0.020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	95	95	ASTM D785
Tensile Strength, Yield	127 MPa	18500 psi	ASTM D638
Flexural Yield Strength	191 MPa	27700 psi	ASTM D790
Izod Impact, Notched	1.18 J/cm	2.20 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	228 °C	442 °F	ASTM D648
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Dielectric Constant	3.5 @Frequency 60 Hz	3.5 @Frequency 60 Hz	ASTM D150

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China